

QUICKSEAL

MP 500

QuickSeal MP 500 is an instant curing flexible Waterproofing membrane that can be built to any thickness in one application.

QuickSeal MP 500 is an economical alternative to QuickSeal PP 350 for applications that are not subject to extreme climatic conditions.

QuickSeal MP 500 provides a permanently flexible, seamless Waterproofing solution for a wide range of substrates. Its rapid application and instant curing characteristics enable shorter shut down times than traditional Waterproofing products.

FEATURES

- Excellent cost to benefits ratio
- Extremely fast application time
- Tack free in seconds – walk on in minutes
- Rapid return to service saves time and money
- Seamless Waterproofing. No welding of joints – totally seamless
- Excellent adhesion to nearly all substrates - concrete, steel, aluminium, wood, foam etc. Can transgress multiple substrate types in one application
- Good tensile and structural strength
- No need to use protector boards when back filling
- 100% solids, VOC-free, Solvent free
- Good abrasion resistance
- Good impact resistance
- Excellent thermal stability

TYPICAL USES

- Large scale Waterproofing for Commercial, Industrial & manufacturing facilities Waterproofing of high impact areas. – Plant rooms, trafficable roof decks Waterproofing for areas exposed to high wind abrasion
- Waterproofing of water features, pools and ponds
- Under concrete screed Waterproofing of large scale podium decks Bridge, street and tunnel construction Waterproofing
- Waterproofing and containment applications where high humidity and high levels of residual moisture are not factors to be considered during application

QUICKSEAL

MP 500

PROCESSING PROPERTIES

INFORMATION ABOUT THE USE OF THE PRODUCT

	DATA
Mixing ratio of Comp. A to Comp. B	1 : 1 by volume
Material consumption [kg/m ² /1mm]	Approx. 1.0
Recommended thickness [mm]	Minimum: 1.0 Maximum: indefinite
Gel time at 25°C [sec.]	10 - 15(dependent on ambient and substrate temperature)
Tack Free-Time at 25°C [sec.]	15 - 30 (dependent on ambient and substrate temperature)
Over coat cycle [h]	0 - 12 Hours (without prep and priming)
Curing/loading after [h]	Walkable: 1 Mechanical: 2-4 Chemical: 12-24
Temperature range for application (ambient) [°C]	0- +50
Temperature range for application (substrate) [°C]	
Material Temperature (Preconditioning) [°C]	25 - 30
Material Temperature (Spraying) [°C]	65 - 75
Maximal relative air humidity for application [%]	80 - 85
Pay attention to the dew point limit	min. 3K > DP (dew point)

PHYSICAL PROPERTIES

INFORMATION ABOUT THE USE OF THE PRODUCT

	DATA	
Chemical Base	-	Comp. A: MDI-Prepolymer Comp. B: Polyolamin Mixture
VOC-content	DIN EN ISO 11890-1 / ASTM D-1259	0%
Solids content	DIN EN 827 / ASTM D-2697	100%
Color	-	Straw / Brownish colour un-pigmented Other colours on request
Viscosity [mPa*s] @ 25° C	DIN EN ISO 2884-2 / ASTM D-4878	Comp. A: 300 – 900 Comp. B: 700 – 1.200
Density [g/cm ³] @ 20° C	DIN EN ISO 2811-2 / ASTM D-1217	Comp. A: 1,09 – 1,13 Comp. B: 0,99 – 1,03
Density [g/cm ³]	EN ISO 1183 / ASTM D-792	0,99 ± 0,02
Tensile strength [MPa]		≥13
Modul [MPa]	ASTM D-412	100% elongation ≥ 7 300% elongation: ≥ 10
Elongation at break [%]		450
Hardness [Shore A]		89 ± 5
Hardness [Shore D]	ISO 868 / ASTM D-2240	35 ± 5
Rebound resilience [%]	ISO 4662 / ASTM D-7121	≥ 38
Tear growth resistance[N/mm]	ISO 34-1 method A	≥ 17
Volume abrasion [mm ³]	DIN ISO 4649	no datas available

PHYSICAL PROPERTIES

INFORMATION ABOUT THE USE OF THE PRODUCT

	DATA	
Taber Abrasion [mg]	ASTM D-4060	< 10 (Wheel CS17 / 1.000g / 1000 Cycles) < 110 (Wheel H18 / 1.000g / 1000 Cycles)
Fire Protection Classification	ASTM E-108	Class A (Spread of flame/ slope 1:12)
Peel off strength [N/mm]	ISO 813 / ASTM D-903	Concrete: ≥ 3 Steel: ≥ 6
Pull off strength [N/mm ²]	DIN EN ISO 4624 / ASTM D-4541	Concrete: ≥ 1,5 Steel: ≥ 4
Min. Process temp. [°C]	ISO 11346 / ASTM D-2485	- 40
Max. Process temp. [°C]		Wet: 50 Dry: 110 Peak temperature dry: 130
Heat Conductivity [W/m*K]	-	0,245
Surface resistance [Ohm]	DIN IEC 60167	≥ 1,0*10 ¹¹
Volume resistance [Ohm]	DIN IEC 60093	
Storage conditions [°C]	DIN EN 12701	10 – 30 (in closed original drums, stored at dry and well ventilated place; beware of freezing)
Shelf life	-	Approximately 12 months

APPLICATION NOTES

The gel times and tack free times depend on the surrounding climatic conditions and the temperature of the substrate, e.g. ambient temperature, substrate temperature, relative humidity and ventilation etc.

Therefore the data specified above can only be used as a guide.

FORM OF DELIVERY

Please see our price list for respective packaging units.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, at the time of printing. However the accuracy, completeness and repeatability of said tests results are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and tests, to determine the suitability of the product / system for his own particular project and application. User assumes all risk and liability resulting from his use of this product / system. We do not suggest or guarantee that any hazards listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or incorrect use of the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and standard application procedures. Test performance results were obtained in a controlled environment and the manufacturer makes no claim that these tests or any other tests, accurately represent all environments.

ISSUE DATE: MARCH 2020

This technical specification supersedes all previous data sheets.